

報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 1 of 9

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as):

Quantity)

樣品保存方式(Sample Packaging) : 常溫 (AMBIENT TEMP.)

樣品型號(Style/Item No.) : 樣品批號(Lot. No.) :

樣品材質(Sample Material) : PET/VMPET/LLDPE

送樣廠商(Sample Submitted By) : 勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

送樣廠商地址/電話/聯絡人(Company : 新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST.,

Add/Tel/Contact Person) NEW TAIPEI CITY 242, TAIWAN (R.O.C.)) / 02-22032266 / -

製造日期(Manufacturing Date) : -有效日期(Expiry Date) : -

原產國(Country of Origin) : 台灣 (TAIWAN)

收件日(Sample Receiving Date) : 2022/12/29

測試期間(Testing Period) : 2022/12/29 to 2023/01/09

測試需求 (Test Requested)

- (1) 依據客戶指定,參考中華民國食品器具容器包裝衛生標準 (102.08.20部授食字第1021350146號令修正) 進行測試。 測試項目請參閱測試結果表格。 (As specified by client, with reference to Sanitation Standard for Food Utensils, Containers and Packages (MOHW Food No. 1021350146, amended on 2013/08/20) to conduct test. Please refer to the result table(s) for testing item(s).)
- (2) 依據客戶指定,參考中華民國食品安全衛生管理法 (108.06.12) 第26條進行測試。測試項目請參閱測試結果表格。 (As specified by client, with reference to Act Governing Food Sanitation Article 26 (amended and promulgated on 2019/06/12) to conduct test. Please refer to the result table(s) for testing item(s).)

測試結果 (Test Results) : 請見下一頁。(Please refer to next page(s).)

蕭志祥

化學實驗室 - 台北 台灣檢驗科技股份有限公

報告簽署人





This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chyuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



測試報告

Test Report

報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 2 of 9

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

測試部位敘述(Test Part Description)

No.1 : 軟性包材(整體樣品) (FLEXIBLE PACKAGING (WHOLE SAMPLE))

No.2 : 軟性包材(與食物接觸面) (FLEXIBLE PACKAGING (FOOD CONTACT SIDE))

測試結果(Test Results)

(1)

測試項目 (Tost Hom(s))	測試項目 測試方法 (Test Item(s)) (Method)	單位 (Unit)	LOQ/ LOD	結果 (Result)		食品衛生 法規
(Test itelli(s))	(Method)		200	No.1	No.2	(Limit)
★鉛 / Lead (Pb)		ppm	5	n.d.		100
★鎘 / Cadmium (Cd)		ppm	0.5	n.d.		100
★鄰苯二甲酸丁苯甲酯 (正庚烷, 25℃, 1小時) / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7) (n-Heptane, 25℃, 1 hr)		ppm	0.05		n.d.	30
★鄰苯二甲酸二丁酯 (正庚烷, 25℃, 1小時) / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2) (n-Heptane, 25℃, 1 hr)		ppm	0.05		n.d.	0.3
★鄰苯二甲酸二異壬酯 (正庚烷, 25℃, 1小時) / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0) (n-Heptane, 25℃, 1 hr)	具、容器、包裝檢驗方法-塑膠類 之檢驗。 / Methods of Test for Food Utensils, Containers and	ppm	0.5	1	n.d.	9
★鄰苯二甲酸二異癸酯 (正庚烷, 25℃, 1小時) / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1) (n-Heptane, 25℃, 1 hr)		ppm	0.5		n.d.	9
★鄰苯二甲酸二(2-乙基己基)酯 (正庚烷, 25°C, 1小時) / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7) (n- Heptane, 25°C, 1 hr)		ppm	0.05		n.d.	1.5
★己二酸二(2-乙基己基)酯 (正庚烷, 25℃, 1 小時) / DEHA (Di-2-ethylhexyl Adipate) (CAS No.: 103-23-1) (n-Heptane, 25℃, 1 hr)		ppm	0.05		n.d.	18

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chvuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 3 of 9

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

(1)

測試項目 (Test Item(s))	測試方法 (Method)	單位 (Unit)	LOQ/ LOD	結乳 (Resi		食品衛生 法規
(Test item(s))	(Metriod)	(01111)	LOD	No.1	No.2	(Limit)
★鄰苯二甲酸二(2-乙基己基)酯 / DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81- 7)	CNS 15138-1 · Z8139-1 : 塑膠製品中鄰苯二甲酸酯類塑化劑試驗法-第1部-氣相層析質譜法。 / CNS 15138-1 Z8139-1 Method of test for determination of phthalates plasticizers in plastic products - Part 1: Gas chromatography/mass spectrometry.	%	0.003	n.d.	1	0.1
★鄰苯二甲酸二丁酯 / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2)		%	0.003	n.d.		0.1
★鄰苯二甲酸丁苯甲酯 / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)		%	0.003	n.d.		0.1
★鄰苯二甲酸二異癸酯 / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1)		%	0.01	n.d.		0.1
★鄰苯二甲酸二異壬酯 / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0)		%	0.01	n.d.		0.1
★鄰苯二甲酸二甲酯 / DMP (Dimethyl phthalate) (CAS No.: 131-11-3)		%	0.003	n.d.		0.1
★鄰苯二甲酸二正辛酯 / DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)		%	0.003	n.d.		0.1
★鄰苯二甲酸二乙酯 / DEP (Diethyl phthalate) (CAS No.: 84-66-2)		%	0.003	n.d.		0.1
★高錳酸鉀消耗量-(水, 95°C, 30分鐘) / Potassium permanganate consumption- (water, 95°C, 30 min)	衛生福利部107.09.17衛授食字第 1071901780號公告修正食品器 具、容器、包裝檢驗方法-聚乙烯 塑膠類之檢驗。 / Methods of Test for Food Utensils, Containers and Packages - Test of Polyethylene (PE) Plastic Products (MOHW Food No. 1071901780 announced, September 17, 2018).	ppm	3		n.d.	10
★重金屬(以鉛計)-(4%醋酸, 95°C, 30分鐘) / Heavy metal (as Pb)-(4% acetic acid, 95°C, 30 min)		ppm	-		<1	1

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chvuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 4 of 9

勵億塑膠股份有限公司(LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

(1)

測試項目 (Test Item(s))		單位 LOQ (Unit) LOD	LOQ/	結果 (Result)		食品衛生 法規
(Test itelli(s))	(Metriod)			No.1	No.2	(Limit)
★蒸發殘渣-(水, 95℃, 30分鐘) / Evaporation residue-(water, 95℃, 30 min)	衛生福利部107.09.17衛授食字第	ppm	3		n.d.	30
★蒸發殘渣-(4%醋酸, 95°C, 30分鐘) / Evaporation residue-(4% acetic acid, 95°C, 30 min)	塑膠類之檢驗。 / Methods of	ppm	3		n.d.	30
★蒸發殘渣-(正庚烷, 25℃, 1小時) / Evaporation residue-(n-Heptane, 25℃, 1 hr)	Test for Food Utensils, Containers and Packages - Test of Polyethylene (PE) Plastic Products (MOHW Food No.	ppm	3		n.d.	150 (*2)
★蒸發殘渣-(20%酒精, 60°C, 30分鐘) / Evaporation residue-(20% alcohol, 60°C, 30 min)	1071901780 announced, September 17, 2018).	ppm	3		n.d.	30

(2)

測試項目 測試方法 (Test Item(s)) (Method)	測試方法 (Method)	單位 (Unit)	LOQ/ LOD	結果 (Result)		食品衛生 法規
(Test item(s))	s)) (Method) (Onit)	(OIIII)		No.1	No.2	(Limit)
★耐熱性試驗 / Heat Tolerance (100℃, 1 h)	衛生福利部106.11.13衛授食字第1061902219號公告修正塑膠類食品器具容器包裝之耐熱溫度標示符合性試驗方法。/ Methods of Test for Labeling Conformance of Heat Tolerance of Plastic Food Utensils, Containers and Packages (MOHW Food No. 1061902219 announced, November 13, 2017).	-	-	功能性正常 ·無變褪色 / No appearance change	-	功能性正常 ·無變褪色, No appearance change

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chvuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 5 of 9

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

備註(Note):

- 1. 檢驗報告僅就委託者之委託事項提供檢驗結果,不對產品合法性做判斷。(The test report merely reflects the test results of the consigned matters of the client and is not a certification of the legitimacy of the related products.)
- 2. 本檢驗報告之所有檢驗內容,均依委託事項執行檢驗,如有不實,願意承擔完全責任。(All contents in the test report are conducted according to the customer-specified items. If there is any falsehood, we are willing to take corresponding responsibility.)
- 3. 本報告不得分離或擷錄使用。(The report is invalid if it is partly reproduced or used.)
- 4. mg/kg = ppm; 0.1wt% = 1000 ppm
- 5. LOQ = 定量極限・若該測試項目屬於定量分析則以「LOQ」表示; LOD = 偵測極限・若該測試項目屬於定性分析則以「LOD」表示。(LOQ = Limit of Quantification, for quantitative analyses; LOD = Limit of Detection, for qualitative analyses.)
- 6. n.d. = Not Detected (未檢出) = Less than (小於) LOQ/LOD
- 7. "-" = Not Regulated (無規格值)
- 8. "---" = Not Conducted (未測項目)
- 9. (*2): 針對加工及調理過程溫度100℃以下之產品。 (For the products which are heated to not higher than 100℃ during food processing and cooking.)
- 10. 測試項目名稱旁有★者,為本實驗室通過衛生福利部認證項目。 (The test method marked with ★ is accredited by MOHW.)
- 11. 法規標準值係依據衛生福利部102年08月20日部授食字第1021350146號令 食品器具容器包裝衛生標準之法規限值。 (The limit value(s) is/are according to "Sanitation Standard for Food Utensils, Containers and Packages (MOHW Food No. 1021350146, amended on 2013/08/20)", Ministry of Health and Welfare of Taiwan.)
- 12. 法規標準值係依據衛生福利部108年06月12日總統令 食品安全衛生管理法第26條之法規規定。 (The limit value(s) is/are according to "Act Governing Food Sanitation Article 26 (amended and promulgated on 2019/06/12)", Ministry of Health and Welfare of Taiwan.)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



報告編號(No.): HTF22C00844 報告日期(DATE): 2023/01/09

頁數(PAGE): 6 of 9

勵億塑膠股份有限公司(LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

*照片中如有箭頭標示,則表示為實際檢測之樣品/部位。 * (The tested sample / part is marked by an arrow if it's shown on the photo.)

HTF22C00844 NO.1



HTF22C00844 NO.2



** 報告結尾 (End of Report) **

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Term and-Conditions. Attention is drawn to the limitation of liability, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chyuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 7 of 9

勵億塑膠股份有限公司(LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

以下為申請廠商委託測試項目、測試方法、定量/偵測極限:

(The information requested from client is shown as below:)

HTF22C00844

測試項目	測試方法	LOQ/LOD
(Test Items)	(Method)	204/202
★鉛 / Lead (Pb) ★鎘 / Cadmium (Cd) ★鄰苯二甲酸丁苯甲酯 (正庚烷, 25°C, 1小時) / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7) (n-Heptane, 25°C, 1 hr) ★鄰苯二甲酸二丁酯 (正庚烷, 25°C, 1小時) / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2) (n-Heptane, 25°C, 1 hr) ★鄰苯二甲酸二異壬酯 (正庚烷, 25°C, 1小時) / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0) (n-Heptane, 25°C, 1 hr) ★鄰苯二甲酸二異癸酯 (正庚烷, 25°C, 1小時) / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1) (n-Heptane, 25°C, 1 hr) ★鄰苯二甲酸二(2-乙基己基)酯 (正庚烷, 25°C, 1小時) / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7) (n-Heptane, 25°C, 1 hr) ★己二酸二(2-乙基己基)酯 (正庚烷, 25°C, 1 小時) / DEHA (Di-2-ethylhexyl Adipate) (CAS No.: 103-23-1) (n-Heptane, 25°C, 1 hr)	衛生福利部107.10.04衛授食字第 1071901983號公告修正食品器具、容 器、包裝檢驗方法-塑膠類之檢驗。 / Methods of Test for Food Utensils, Containers and Packages - Test of Plastics (MOHW Food No. 1071901983 announced, October 04, 2018).	詳見測試結果之定量/偵測極限。 (Please refer to the result table above.)
★鄰苯二甲酸二(2-乙基己基)酯 / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7) ★鄰苯二甲酸二丁酯 / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2) ★鄰苯二甲酸丁苯甲酯 / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)	CNS 15138-1 · Z8139-1 : 塑膠製品中鄰苯二甲酸酯類塑化劑試驗法-第1部-氣相層析質譜法。 / CNS 15138-1 Z8139-1 Method of test for determination of phthalates plasticizers in plastic products - Part 1: Gas chromatography/mass spectrometry.	

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chyuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



測試報告

報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 8 of 9

Test Report

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

以下為申請廠商委託測試項目、測試方法、定量/偵測極限:

(The information requested from client is shown as below :)

HTF22C00844

測試項目	測試方法	LOQ/LOD	
(Test Items)	(Method)	204/202	
★鄰苯二甲酸二異癸酯 / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1)			
★鄰苯二甲酸二異壬酯 / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0)	CNS 15138-1 · Z8139-1 : 塑膠製品中鄰苯二甲酸酯類塑化劑試驗法-第1部-氣相層析質譜法。 / CNS 15138-1 Z8139-1		
★鄰苯二甲酸二甲酯 / DMP (Dimethyl phthalate) (CAS No.: 131-11-3)	Method of test for determination of phthalates plasticizers in plastic products - Part 1: Gas chromatography/mass spectrometry.		
★鄰苯二甲酸二正辛酯 / DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)			
★鄰苯二甲酸二乙酯 / DEP (Diethyl phthalate) (CAS No.: 84-66-2)			
★高錳酸鉀消耗量-(水, 95°C, 30分鐘) / Potassium permanganate consumption-(water, 95°C, 30 min)		詳見測試結果之定量/偵測極限。 (Please refer to the result table	
★重金屬(以鉛計)-(4%醋酸, 95°C, 30分鐘) / Heavy metal (as Pb)-(4% acetic acid, 95°C, 30 min)	衛生福利部107.09.17衛授食字第	above.)	
★蒸發殘渣-(水, 95℃, 30分鐘) / Evaporation residue-(water, 95℃, 30 min)	Methods of Test for Food Utensils,		
★蒸發殘渣-(4%醋酸, 95℃, 30分鐘) / Evaporation residue-(4% acetic acid, 95℃, 30 min)		°C, Containers and Packages - Test of Polyethylene (PE) Plastic Products	
★蒸發殘渣-(正庚烷, 25℃, 1小時) / Evaporation residue-(n-Heptane, 25℃, 1 hr)			
★蒸發殘渣-(20%酒精, 60°C, 30分鐘) / Evaporation residue-(20% alcohol, 60°C, 30 min)			

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chvuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei Citv, Taiwan



測試報告

報告編號(No.): HTF22C00844

報告日期(DATE): 2023/01/09

頁數(PAGE): 9 of 9

Test Report

勵億塑膠股份有限公司 (LIYIH PLASTICS CO., LTD.)

新北市新莊區民安東路178號 (NO.178, MIN-AN E. RD., XINZHUANG DIST., NEW TAIPEI CITY 242, TAIWAN (R.O.C.))

以下為申請廠商委託測試項目、測試方法、定量/偵測極限:

(The information requested from client is shown as below:)

HTF22C00844

測試項目 (Test Items)	測試方法 (Method)	LOQ/LOD
★耐熱性試驗 / Heat Tolerance (100°C, 1 h)	衛生福利部106.11.13衛授食字第 1061902219號公告修正塑膠類食品器具 容器包裝之耐熱溫度標示符合性試驗方 法。/ Methods of Test for Labeling Conformance of Heat Tolerance of Plastic Food Utensils, Containers and Packages (MOHW Food No. 1061902219 announced, November 13, 2017).	詳見測試結果之定量/偵測極限。 (Please refer to the result table above.)

測試項目名稱旁有★者,為本實驗室通過衛生福利部認證項目。(The test method marked with ★ is accredited by MOHW.)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886 (02)2299 3939 f+886 (02)2299 3237 No. 25, Wu Chyuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan